Turkish Online Journal of Qualitative Inquiry (TOJQI) Volume 12, Issue 10, October 2021: 3775-3783

EVALUATE THE FAILURE RATES BETWEEN OCCLUSAL AND OCCLUSOPROXIMAL AMALGAM AND COMPOSITE RESIN OF POSTERIOR RESTORATIONS: A SYSTEMATIC REVIEW AND META-ANALYSIS

Dorara Dortaj¹, Dorsa Khosravi², Yasser Samadi³, Zahra Jahanshahiafshar⁴

¹Post Graduate Student, Department of Operative Dentistry, School of Dentistry, Tehran University of Medical Sciences, Tehran, Iran.

²Assistant Professor, Department of Operative Dentistry, School of Dentistry, Kerman University of Medical Sciences, Kerman, Iran.

³Postgraduate Student, Department of Endodontics, School of Dentistry, Shiraz University of Medical Science, Shiraz, Iran.

⁴Postgraduate student, Department of Oral and Maxillofacial Radiology, Faculty of Dentistry, Babol University of Medical Sciences, Babol, Iran.

Abstract :

the aim of present study was compared Failure Rates between occlusal and occlusoproximal amalgam and composite resin of posterior restorations.

From the electronic databases, PubMed, Scopus, LILACS, Web of Science, EBSCO, LIVIVO, and Embase have been used to perform a systematic literature over the last 20 years between 2001 and September 2021. Risk ratio with 95% confidence interval, fixed effect model and Mantel-Haenszel method were calculated. The Meta analysis have been evaluated with the statistical software Stata/MP v.16 (The fastest version of Stata).

113 studies were selected to review the abstracts, the full text of 19 studies was reviewed. Finally, five studies were selected. Risk ratio of restoration failure rate and secondary caries between amalgam and composite resin was 0.14 (RR, 0.14 95 % CI 0.10, 0.17; p=0.00) and 0.15 (RR, 0.15 95 % CI 0.11, 0.18; p=0.00), respectively. Composite resin significantly increased the risk of restoration failure and secondary caries.

meta-analysis showed that the failure rate in composite resin restorations is higher than amalgam in the restoration of posterior teeth. Present study suggested that amalgam was better than composite resin restorations. More RCT studies are needed to provide sufficient and stronger evidence.

Keywords: amalgam, composite resin, posterior restorations

Introduction :

Amalgam has been the traditional material for filling cavities in posterior teeth for the last 150 years and, due to its effectiveness and cost, amalgam is still the restorative material of choice in certain parts of the world. In recent times, however, there have been concerns over the use of amalgam restorations (fillings), relating to the mercury release in the body and the environmental impact following its disposal. Resin composites have become an esthetic alternative to amalgam restorations and there has been a remarkable improvement of its mechanical properties to restore posterior teeth (1). With respect to amalgam restorations, failures are more often found in premolar teeth (34%) than in molars (27%)(2). Under optimal conditions, Class I and II amalgam restorations have a median survival time, between 57 and 70 years according to Mitchell et al.,2007 (3). Few RCT studies have been performed to evaluate the lifespan of restorations, especially in posterior teeth. There is insufficient evidence in this regard, as the size of the cavities, experience and expertise, type of consumables may have a significant impact on restoration performance. Therefore, the present study compared Failure Rates between occlusal and occlusoproximal amalgam and composite resin of posterior restorations.

Methods :

Search strategy :

From the electronic databases, PubMed, Scopus, LILACS, Web of Science, EBSCO, LIVIVO, and Embase have been used to perform a systematic literature over the last twenty years between 2001 and September 2021. The reason for choosing studies in the last ten years is to be able to provide sufficient evidence in this area and use newer studies. Therefore, a software program (Endnote X8) has been utilized for managing the electronic titles. Searches were performed with mesh terms:

((((((("Dental Restoration, Permanent/adverse effects"[Mesh] OR "Dental Restoration, Permanent/classification"[Mesh] OR "Dental Restoration, Permanent/instrumentation"[Mesh] OR "Dental Restoration, Permanent/methods"[Mesh] OR "Dental Restoration, Permanent/statistics and numerical data"[Mesh])) OR "Dental Restoration, Permanent"[Mesh]) OR "Dental Occlusion"[Mesh]) AND "Bicuspid"[Mesh]) OR ("Molar"[Mesh] OR "Molar, Third"[Mesh])) AND "Failure of Tooth Eruption, Primary" [Supplementary Concept]) AND "Survival Rate"[Mesh]) OR "Contraceptive Effectiveness"[Mesh].

This systematic review has been conducted on the basis of the key consideration of the PRISMA Statement– Perfumed Reporting Items for the Systematic Review and Meta-analysis(4), and PICO strategy (Table1).

Selection criteria :

Inclusion criteria: Randomized controlled trials studies, controlled clinical trials; Prospective and retrospective cohort studies; in human; molar and premolar; posterior restorations; in English. In vitro studies, case studies, case reports and reviews were excluded from the study.

PICO	Description
strategy	
Р	Population/ Patient: human participants with posterior restorations
E	Intervention: amalgam

Table 1. PICO OR PECO strategy.

С	Comparison: composite resin
0	Outcome: Failure Rate

Data Extraction and analysis method

The data were extracted from the research included study. Years, study design, Number of patients, sample size, mean of age, cavity, number of restorations and follow-up period.

The quality of randomized studies included was assessed using Collaboration's tool(5). The scale scores for low risk was 1 and for High and unclear risk was 0. Scale scores range from 0 to 6. A higher score means higher quality. Newcastle-Ottawa Scale (NOS) (6) used to assessed quality of the cohort studies and case-control studies, This scale measures three dimensions (selection, comparability of cohorts and outcome) with a total of 9 items. In the analysis, any studies with NOS scores of 1-3, 4-6 and 7-9 were defined as low, medium and high quality, respectively.

For Data extraction, two reviewers blind and independently extracted data from abstract and full text of studies that included. Prior to the screening, kappa statistics was carried out in order to verify the agreement level between the reviewers. The kappa values were higher than 0.80.

Risk ratio with 95% confidence interval (CI), fixed effect model and Mantel-Haenszel method were calculated. Random effects were used to deal with potential heterogeneity and I² showed heterogeneity. I² values above 50% signified moderate-to-high heterogeneity. The Meta analysis have been evaluated with the statistical software Stata/MP v.16 (The fastest version of Stata).

Results :

In the initial review of the existing literature and based on keywords related to the subject of the study, first 113 studies were found in databases. After deleting similar and duplicate studies, the abstract of 78 studies was reviewed. At this stage, studies that did not meet the inclusion criteria were excluded from the study (59 studies). The full text of 19 studies was reviewed and 14 studies were excluded, finally five studies were selected.





Studies included in systematic review and meta-analysis (n=5)

Figure 1. Flowchart of the literature search and selection criteria

Study. Year	Study design	Number of		Type and size of	Type of	Observation
		restorations		Cavity	Tooth	Period
		amalgam composite				
			resin			
Kemaloglu et al.,2016	RCT	20	20	Occlusal and	posterior	3
(7)				occlusoproximal	teeth	
Kim et al.,2013 (8)	Retrospective	139	175	Occlusal and	posterior	5
				occlusoproximal	teeth	
Bernardo et al., 2007	RCT	856	892	Occlusal and	Premolar	7
(9)				occlusoproximal,	and molar	
				Small, medium,		
				large		
Levin et al., 2007 (10)	Prospective	557	93	Occlusal and	posterior	1
				occlusoproximal	teeth	
Wilson et al., 2002	RCT	52	52	Occlusal and	Premolar	1
(11)				occlusoproximal,	and molar	
				medium		

Table2. Summary of characteristics of included studies

Table 3. Risk of bias assessment (Randomized clinical trials).

Study	Random generation of sequences	Concealment of Allocation	Blinding of participants and personnel	Blinding of outcome assessment	Incomplete data on outcomes	Selective reporting	Total score
Kemaloglu et al., 2016 (7)	?	+	+	•	+	+	4
Bernardo et al., 2007 (9)	?	+	+	•	+	+	4
Wilson et al., 2002 (11)	?	+	+		+	+	4

Low (+), unclear (?), high (-)

	Se	lection	n (5 sc	ore)	Comparabilit y (2 score)	Outcon (2 score	ne e)	
Study. Years	representative sample	Sample size	Non respondents	Ascertainment of the exposure	Based on design and analysis	Assessment of outcome	Statistical test	Total score
Kim et al.,2013 (8)	1	1	1	1	2	1	1	8
Levin et al., 2007 (10)	1	1	1	0	1	1	1	6

Table4. Risk of bias assessment (NOS tool)

Characteristics

Five studies (3 Randomized clinical trials, one Retrospective study and one Prospective study) have been included in present article. The Number of restorations in amalgam group and composite resin group was 1624 and 1232, respectively; a total was 2856. Other characteristics of the selected studies are reported in Table 2.

Bias assessment

According to Collaboration's tool, all studies had a total score of 4/6; and According to NOS tool, one study had a total score of 8/9 and one study a total score of 6/9. Four studies had moderate risk of bias and one study had low risk of bias or high quality (Table 3 and 4).

Restoration failure rate

Risk ratio of restoration failure rate between amalgam and composite resin was 0.14 (RR, 0.14 95 % CI 0.10, 0.17; p=0.00) with high heterogeneity ($I^2 = 93.08\%$; p=0.00) (Figure 2). This result shows statistically significant difference of restoration failure rate between amalgam and composite resin; composite resin significantly increased the risk of failure. In amalgam and composite resin the number of Restoration failure was 157/1624 (9.66%) and 236/1202 (19.63%), respectively (Figure 2).

Restoration failure rate	Amal	gam	Composi	Composite resin		Log Risk-Ratio	Weight		
Study	success	failure	success	failure				with 95% CI	(%)
Kemaloglu et al.,2016	12	8	10	10				0.18 [-0.38, 0.75]	1.00
Kim et al.,2013	106	33	125	50				0.07 [-0.07, 0.20]	11.07
Bernardo et al., 2007	808	48	763	129				0.10 [0.07, 0.13]	74.78
Levin et al., 2007	490	67	46	47				0.58 [0.37, 0.78]	7.89
Wilson et al., 2002	51	1	52	0		+		-0.02 [-0.07, 0.03]	5.25
Overall						٠		0.14 [0.10, 0.17]	
Heterogeneity: $I^2 = 93.0$	8%, H ² =	14.45							
Test of $\theta_i = \theta_j$: Q(4) = 57	.79, p = 0	.00							
Test of θ = 0: z = 7.81, g	0.00 = 0.00								
					5	0	.5	1	

Fixed-effects Mantel-Haenszel model

Figure 2. The Forest plot showed restoration failure rate between amalgam and composite resin

Secondary caries :

Risk ratio of secondary caries between amalgam and composite resin was 0.15 (RR, 0.15 95 % CI 0.11, 0.18; p=0.00) with high heterogeneity (I² =95.95%; p=0.00) (Figure 3). This result shows statistically significant difference of Secondary caries between amalgam and composite resin; composite resin significantly increased the risk of secondary caries. In amalgam and composite resin the number of event secondary caries was 75/1413 (5.3%) and 153/985 (15.53%), respectively (Figure 3).



Figure 2. The Forest plot showed secondary caries between amalgam and composite resin

Fracture :

Risk ratio of event fracture between amalgam and composite resin was -0.01 (RR, -0.01 95 % CI -0.02, 0.01; p=0.31) with low heterogeneity (I² =47.08%; p=0.15) (Figure4). This result shows no statistically significant difference of event fracture between amalgam and composite resin; In amalgam and composite resin the number of event fracture was 39/1465 (2.6%) and 17/1037 (1.6%), respectively (Figure3).

Fracture	Amalg	gam	Composite resin		Composite resin			Log Risk-Ratio	Weight
Study	success	failure	success	failure		with 95% CI	(%)		
Bernardo et al., 2007	840	16	876	16		-0.00 [-0.01, 0.01]	80.32		
Levin et al., 2007	535	22	92	1		-0.03 [-0.06, -0.00]	14.76		
Wilson et al., 2002	51	1	52	0		-0.02 [-0.07, 0.03]	4.92		
Overall					•	-0.01 [-0.02, 0.01]			
Heterogeneity: $I^2 = 47.0$	08%, H ² =	1.89							
Test of $\theta_i = \theta_j$: Q(2) = 3.	.78, p = 0.	15							
Test of θ = 0: z = -1.01,	p = 0.31								
				ا 	105 0	¬ 05			
Fixed-effects Mantel-Ha	enszel mo	del							

Discussion :

The aim of current systematic review and meta-analysis study was evaluate the Failure Rates between occlusal and occlusoproximal amalgam and composite resin of posterior restorations. The use of resin composite for routine restoration of cavities in posterior teeth is now commonplace, and will increase further following the Minamata Agreement and patient requests for tooth-coloured restorations in their posterior teeth. It is therefore

relevant to evaluate the published survival rates of such restorations (12). As reported in previously published data, secondary caries is the main reason for failure of both resin composites and amalgam restorations (9, 13). In present study failure rate and Secondary caries was more noticeable in resin composites than amalgams. Studies concluded that more extensive restorations showed reduced clinical performance, especially the survival rates decrease as the size of restorations increase(14, 15). Studies compared different composite resin brands (16-18), amalgams with composite resins (9), and different amalgams (19). Afrashtehfar et al., 2017 in a systematic review included Five RCT and nine observational studies Data obtained from the RCT showed that, regardless of the amount of remaining tooth structure, amalgams presented better outcomes than composite resins(20); these results are consistent with the present study. Burke et al., 2019 evaluate survival rates of resin composite restorations in loadbearing situations in posterior teeth, the result showed posterior composites may provide restorations of satisfactory longevity and with survival rates generally similar to those published on amalgam restorations. However, the ability of the operator in placing the restoration may have a profound effect (21). Worthington et al., 2021 in a review updated a review originally published in 2014, expanding the scope of the review by undertaking an additional search for harms outcomes. This review synthesises the results of studies that evaluate the long-term effectiveness and safety of amalgam versus composite resin restorations, and evaluates the level of certainty we can have in that evidence (22). A systematic review and meta-analysis by Moraschini et al., 2015 showed composite resin restorations in posterior teeth still have less longevity and a higher number of secondary caries when compared to amalgam restorations(23). Karrabi et al., 2020 showed higher longevity of the amalgam restorations compared to composite resin restorations (24).

Conclusion :

Due to the few studies in this regard and despite the existing limitations, meta-analysis showed that the failure rate in composite resin restorations is higher than amalgam in the restoration of posterior teeth. Since restoration in posterior teeth is directly related to the rate of failure, proper treatment planning should be based on the structure of the remaining teeth. Ignoring this (the amount of tooth structure remaining in the posterior teeth), it is suggested that amalgam works better than composite resin restorations. More RCT studies are needed to provide sufficient and stronger evidence.

References:

- Rasines Alcaraz MG, Veitz-Keenan A, Sahrmann P, Schmidlin PR, Davis D, Iheozor-Ejiofor Z. Direct composite resin fillings versus amalgam fillings for permanent or adult posterior teeth. The Cochrane database of systematic reviews. 2014(3):Cd005620.
- Soares AC, Cavalheiro A. A review of amalgam and composite longevity of posterior restorations. Revista Portuguesa de Estomatologia, Medicina Dentária e Cirurgia Maxilofacial. 2010;51(3):155-64.
- 3. Mitchell RJ, Koike M, Okabe T. Posterior amalgam restorations—usage, regulation, and longevity. Dental Clinics of North America. 2007;51(3):573-89.
- Moher D, Liberati A, Tetzlaff J, Altman DG, Altman D, Antes G, et al. Preferred reporting items for systematic reviews and meta-analyses: the PRISMA statement (Chinese edition). Journal of Chinese Integrative Medicine. 2009;7(9):889-96.

- Higgins J, Altman D, Gøtzsche P, Jüni P, Moher D, Oxman A, et al. Cochrane bias methods group; cochrane statistical methods group. The Cochrane Collaboration's tool for assessing risk of bias in randomised trials BMJ. 2011;343(7829):d5928.
- 6. Stang A. Critical evaluation of the Newcastle-Ottawa scale for the assessment of the quality of nonrandomized studies in meta-analyses. European journal of epidemiology. 2010;25(9):603-5.
- 7. Kemaloglu H, Pamir T, Tezel H. A 3-year randomized clinical trial evaluating two different bonded posterior restorations: Amalgam versus resin composite. European journal of dentistry. 2016;10(01):016-22.
- 8. Kim K-L, Namgung C, Cho B-H. The effect of clinical performance on the survival estimates of direct restorations. Restorative dentistry & endodontics. 2013;38(1):11-20.
- Bernardo M, Luis H, Martin MD, Leroux BG, Rue T, Leitão J, et al. Survival and reasons for failure of amalgam versus composite posterior restorations placed in a randomized clinical trial. The Journal of the American Dental Association. 2007;138(6):775-83.
- 10. Levin L, Coval M, Geiger SB. Cross-sectional radiographic survey of amalgam and resin-based composite posterior restorations. Quintessence International. 2007;38(6).
- 11. Wilson M, Cowan A, Randall R, Crisp R, Wilson N. A practice-based, randomized, controlled clinical trial of a new resin composite restorative: one-year results. Operative Dentistry. 2002;27(5):423-9.
- 12. Burke FT, Mackenzie L, Shortall AC. Survival rates of resin composite restorations in loadbearing situations in posterior teeth. Dental Update. 2019;46(6):524-36.
- 13. Celik C, Arhun N, Yamanel K. Clinical evaluation of resin-based composites in posterior restorations: 12-month results. European Journal of Dentistry. 2010;4(01):057-65.
- 14. McCracken MS, Gordan VV, Litaker MS, Funkhouser E, Fellows JL, Shamp DG, et al. A 24-month evaluation of amalgam and resin-based composite restorations: Findings from The National Dental Practice-Based Research Network. The Journal of the American Dental Association. 2013;144(6):583-93.
- 15. Setcos J, Staninec M, Wilson N. Bonding of amalgam restorations: existing knowledge and future prospects. Operative dentistry. 2000;25(2):121-9.
- 16. Krämer N, García-Godoy F, Reinelt C, Feilzer AJ, Frankenberger R. Nanohybrid vs. fine hybrid composite in extended Class II cavities after six years. Dental Materials. 2011;27(5):455-64.
- 17. Manhart J, Chen H-Y, Hickel R. Clinical evaluation of the posterior composite Quixfil in class I and II cavities: 4-year follow-up of a randomized controlled trial. J Adhes Dent. 2010;12(3):237-43.
- 18. Shi L, Wang X, Zhao Q, Zhang Y, Zhang L, Ren Y, et al. Evaluation of packable and conventional hybrid resin composites in Class I restorations: Three-year results of a randomized, double-blind and controlled clinical trial. Operative dentistry. 2010;35(1):11-9.
- 19. PLASMANS PJJM, VAN 'T HOF MA. A 4-year clinical evaluation of extensive amalgam restorations description of the failures. Journal of Oral Rehabilitation. 1993;20(6):561-70.
- 20. Afrashtehfar KI, Emami E, Ahmadi M, Eilayyan O, Abi-Nader S, Tamimi F. Failure rate of single-unit restorations on posterior vital teeth: A systematic review. The Journal of Prosthetic Dentistry. 2017;117(3):345-53.e8.
- 21. Burke FJT, Mackenzie L, Shortall AC. Survival rates of resin composite restorations in loadbearing situations in posterior teeth. Dental Update. 2019;46(6):524-36.

- 22. Worthington HV, Khangura S, Seal K, Mierzwinski-Urban M, Veitz-Keenan A, Sahrmann P, et al. Direct composite resin fillings versus amalgam fillings for permanent posterior teeth. The Cochrane database of systematic reviews. 2021;8(8):Cd005620.
- 23. Moraschini V, Fai CK, Alto RM, dos Santos GO. Amalgam and resin composite longevity of posterior restorations: A systematic review and meta-analysis. Journal of Dentistry. 2015;43(9):1043-50.
- 24. Karrabi M SF, Kianipour A. Evaluate the difference in failure rates between amalgam and composite resin posterior restorations. International Journal of Pharmaceutical Research. 2020;12(1):573-9.